

T-308L

For austenite stainless steel (Low carbon, 18%Cr-8%Ni STS)

Classifications

EN ISO 14343-A:2009	: W 19 9 L	JIS Z 3321:2013	: YS308L
EN ISO 14343-B:2009	: SS 308L	KS D 3696:2006	: STSY308L
AWS A5.9-2012	: ER308L		

Description

- TIG welding of 18%Cr-8%Ni austenite stainless steels (AISI STS 301, 302, 304)
- A various application of the petrochemical , nuclear power plant apparatus.
- WRC 1992 FN 3-8 (Chemical Composition of wire, If required)

Typical chemical composition of wire (%)

C	Si	Mn	Ni	Cr
0.02	0.38	1.90	9.77	19.79

Typical mechanical properties of all-weld metal

	Y.S (MPa)	T.S (MPa)	El. (%)	IV (J) 0°C	IV (J) -196°C
AWS A5.9		min. 520	min. 35		
EN ISO 14343	min. 320	min. 510	min. 30		
Example	390	580	44	160	80